Semiconductor   component   with   stress-absorbing
semiconductor layer, and associated fabrication method

5

The   present   invention   relates   to   a   semiconductor
component   with   stress-absorbing   semiconductor   layer,
and   to   an   associated   fabrication   method,   and   in
particular   to   a   sub-100   nanometer   field-effect
10   transistor with fully depleted active region.

As   the   development   of   semiconductor   components
continues,   ever   smaller   feature   sizes   are   desired   with
a   view   to   improving   the   integration   density.   However,
15   certain   limits   are   being   reached   on   account   of   limited
charge   carrier   mobility   in   semiconductor   materials.
Since   an   upper   limit   to   the   charge   carrier   mobility   of
electrons   and   holes   in   a   semiconductor   crystal   is
dependent   on   the   physical   properties   of   the
20   semiconductor   crystal,   the   required   charge   carrier
mobility   cannot   be   established   or   cannot   be   established
with   sufficient   accuracy   in   the   case   of   very   small
feature   sizes   of   a   semiconductor   component.
Furthermore,   what   are   known   as   high-k   gate   dielectrics
25   (dielectrics   with   a   high   dielectric   constant),   which
are   also   required   for   the   increasing   integration
density,   cause   a reduced   charge   carrier   mobility.

Therefore,   what   are   known   as   semiconductor   components
30   with   stress-absorbing   semiconductor   layers   (strained
semiconductors)   have   been   developed,   making   it   possible
to   improve   charge   carrier   mobility   in   a   stress-
absorbing semiconductor crystal.

35   Figure 1 shows a simplified illustration of a crystal
demonstrating   this   effect.   It   is   usual   for   a   stress-
absorbing   or   mechanically   loaded   Si   layer   as   stress-
absorbing   semiconductor   layer   SA   to   be   formed   by
growing   a   thin   crystal   layer   on   a   carrier   crystal,   the

lattice constant of which is different than the lattice constant of the silicon crystal which has been grown on. It is customary for an SiGe crystal layer to be used as the so-called stress generator layer SG, in which case the Ge content can be adjusted and is preferably approx. 20%. This results in a lattice constant for the SiGe crystal SG which is approx. 0.8% greater than the lattice constant of the Si layer SA deposited thereon. These different lattice constants result, in particular for the stress-absorbing Si layer SA, in the mechanical stresses which are represented by the arrows, with the result that ultimately it is possible to establish a better charge carrier mobility on account of the piezoresistance effect in this layer.

To achieve improved insulation properties and thereby a reduced leakage current as well as reduced capacitances in a semiconductor circuit, it is customary to use what are known as SOI (silicon on insulator) substrates, but the technology described above cannot be applied directly to SOI substrates of this nature.

Figure 2 shows a simplified sectional view through an SiGe-on-insulator nMOSFET, as is known, for example, from the literature reference T. Tezuka et al.: "Novel Fully-Depleted SiGe-On-Insulator pMOSFETs with High-Mobility SiGe Surface Channels" IEEE 2001. In this case, an amorphous SiO_2 layer 200 is formed on an Si carrier substrate 100, resulting in a typical SOI substrate. Then, a stress generator layer SG, which in its lower region includes a crystalline Si layer with an SiGe layer subsequently grown on it in order to generate the mechanical stress, is formed at the surface of the SiO_2 layer 200. Then, an Si layer is grown on as stress-absorbing semiconductor layer SA, which on account of the different lattice constants is under a mechanical stress and therefore has an increased charge carrier mobility. Finally, a gate

oxide layer 300 and a polysilicon layer 400 are formed
as control layer, source and drain regions S and D
being formed for connection of the stress-absorbing
semiconductor layer SA which forms a channel region K.

5   However, with a conventional semiconductor component
with stress-absorbing semiconductor layer SA of this
type, it is impossible to further reduce the feature
sizes, in particular in a sub-100nm range, or to
further improve the electrical properties.

10

Therefore, the invention is based on the object of
providing a semiconductor component having a stress-
absorbing semiconductor layer and an associated
fabrication method which has improved electrical

15   properties even in a sub-100nm range.

According to the invention, this object is achieved,
with regard to the semiconductor component, by the
features of patent claim 1 and, with regard to the

20   fabrication method, by the measures of patent claim 8.

In particular by using a crystalline stress generator
layer formed on a carrier material and an insulating
stress transmission layer formed thereon, it is

25   possible for the stresses which are generated and
transmitted to be absorbed in a stress-absorbing
semiconductor layer formed thereon to such an extent
that on the one hand an improved charge carrier
mobility is established and on the other hand improved

30   electrical properties can be achieved in the
semiconductor component.

It is preferable for the stress-absorbing semiconductor
layer to include an intrinsic semiconductor, the

35   thickness of which is less than 1/3 of a length of the
channel region, resulting in a semiconductor component
with a fully depleted semiconductor body. In addition
to the improved charge carrier mobility, this also

results in a reduced off-current with a simple structure.

It is preferable for the stress transmission layer to have a lattice constant which is matched to the second lattice constant of the stress-absorbing semiconductor layer, resulting in excellent transmission properties for the mechanical load or stress.

Furthermore, in this way it is for the first time possible to use gate dielectrics with a high dielectric constant and control layers with a metal gate in semiconductor components with stress-absorbing layers, with the result that an equivalent oxide thickness (EOT) for the gate dielectric can be reduced and excellent gate driving properties can be achieved.

To achieve an excellent starting surface, it is preferable for an Si substrate with a (100) surface orientation and a Si buffer layer deposited thereon to be used as carrier material.

Furthermore, to improve a surface quality, it is also possible for the stress generator layer to be smoothed by means of a molecular beam epitaxy process, resulting in further improved electrical properties for the semiconductor component.

It is preferable for Si to be used as carrier material, for SiGe to be used as stress generator layer, for CaF_2 to be used as stress transmission layer, for Si to be used as stress-absorbing semiconductor layer, for HfO_2 to be used as gate dielectric and for TiN to be used as control layer, with the result that, using standard material, a particularly simple structure and excellent properties in particular with regard to the off-current, the charge carrier mobility, the equivalent oxide thickness, etc. are obtained.

Further advantageous configurations of the invention are characterized in the subclaims.

5   The invention is described in more detail below on the basis of an exemplary embodiment and with reference to the drawing, in which:

Figure 1 shows a simplified illustration of a crystal
10   showing significant effects in stress-absorbing semiconductor layers;

Figure 2 shows a simplified sectional view through a conventional semiconductor component with stress-
15   absorbing semiconductor layer; and

Figures 3A and 3B show simplified sectional views illustrating important method steps involved in the fabrication of a semiconductor component according to
20   the invention with stress-absorbing semiconductor layer.

The invention is described below by way of example on the basis of an nMOSFET as semiconductor component with
25   stress-absorbing semiconductor layer. However, it is not restricted to this application and in the same way also encompasses pMOSFETs and other corresponding semiconductor components which have a stress-absorbing semiconductor layer for the purpose of improving charge
30   carrier mobility.

First of all, in accordance with Figure 3A, a carrier material 1 is provided, which includes, for example, a silicon semiconductor material. Alternatively, however,
35   it is also possible to use any other crystalline and approximately lattice-matched carrier material (e.g. sapphire, etc.).

In particular in order to improve a surface quality, the carrier material 1 may, for example, comprise a semiconductor substrate 1A with a (100) surface orientation, in which case it is preferable to use a Si

5   substrate. To achieve a high-quality starting surface and to bury the interface states at the interface between 1B and 1A, it is possible, in accordance with Figure 3A, by way of example, for a semiconductor buffer layer 1B to be deposited epitaxially, in which

10   case it is preferable for a silicon buffer layer to be deposited by means of a molecular beam epitaxy (MBE) process or a MOCVD (metal organic chemical vapor deposition) process. Particularly when using an MBE process, this treatment step results in a starting

15   surface which has been smoothed to a range of one atom layer. The thickness of the buffer layer 1B is in this case determined only by a processing rate (throughput) and a predetermined starting quality.

20   As an alternative to the smoothing process described above, it is also possible to carry out conventional smoothing processes, such as for example CMP (chemical mechanical polishing) processes.

25   Then, a crystalline stress generator layer SG is formed on the carrier material 1 or the smooth starting surface of the semiconductor buffer layer 1B, the crystal structure of this stress generator layer SG substantially having a first lattice constant for the

30   purpose of generating a mechanical stress in the stress-absorbing semiconductor layer which is subsequently formed.

By way of example, the stress generator layer SG

35   includes a IV-IV semiconductor or a III-V semiconductor. However, it may also include a multilayer sequence and/or change gradually by means of a molecular beam epitaxial, which in turn results in

improved ongrowth properties for the subsequent layers. In particular when an Si layer is used as stress-absorbing semiconductor layer SA, it is preferable for $Si_{1-x}Ge_x$ to be used as semiconductor material for the stress generator layer SG, the Ge content usually being set to from 10 to 50% (x = 0.1-0.5). This results in a lattice constant in the stress generator layer SG which is slightly different than the carrier material and in particular than the stress-absorbing semiconductor layer SA which is subsequently to be formed, this lattice constant of the stress generator layer deviating, for example, by a few percent (less than 10%) at its (final) atom layer on account of its mismatch.

When realizing a sub-100 nanometer semiconductor component, this stress generator layer SG is formed with a typical thickness of 10 to 300 nanometers, preferably using a MOCVD (metal organic chemical vapor deposition) process. Each crystal layer which is subsequently formed with a significantly lower thickness will accordingly orient its lattice constant relative to this top layer.

While in conventional processes the stress-absorbing layer SA is at this point formed directly on the stress generator layer SG, in the process according to the invention a stress transmission layer 2, which transmits the mechanical stress which has been generated and also has insulating properties, is now formed.

Since thermally formed or deposited insulator layers, such as for example oxide layers, have an amorphous structure, they are not in principle suitable as stress transmission layers. By contrast, crystalline insulator layers with a predetermined crystal structure are able to transmit mechanical stresses of this nature which

have been generated in the stress generator layer SG to a following stress-absorbing semiconductor layer SA. Examples of known crystalline insulator layers of this type include CdF_2, CaF_2 and the like.

5

When using a stress-absorbing semiconductor layer consisting of silicon, in particular CaF_2 has particularly good properties, since the lattice constant of CaF_2 is very well matched (for example very similar) to the lattice constant of silicon (lattice constant of CaF_2 = 0.546 nanometer, lattice constant of Si = 0.543 nanometer at room temperature). Furthermore, CaF_2 constitutes an electrical insulator with the highest energy gap (valence band to conduction band = 12eV) of all existing materials. On account of this extraordinarily large energy gap (12 eV), when using CaF_2 it is sufficient to form just a few atom layers at the surface of the stress generator layer SG. Accordingly, it is preferable for an approx. 1 to 2 nanometer thick CaF_2 stress transmission layer 2 to be deposited as a buried insulator by means of, for example, an atomic layer deposition process (ALCVD, atomic layer chemical vapor deposition) or an MBE process.

25

Then, the actual stress-absorbing semiconductor layer SA is formed at the surface of the insulating stress transmission layer 2, with a silicon semiconductor layer preferably being formed as active region, e.g. channel region K, for the semiconductor component. Particularly when producing sub-100 nanometer semiconductor components, in which case field-effect transistors may, for example, have a channel length of 15 nanometers, in this case an intrinsic semiconductor material, i.e. intrinsic silicon, with a thickness d of less than 1/3 of a channel length L is deposited. Accordingly, for a channel length L = 15 nanometers, approx. d = 5 nanometers of intrinsic semiconductor

material are deposited by ALCVD or MOCVD or MBE
processes, resulting in a semiconductor component with
a fully depleted active region or semiconductor body
(fully depleted bodies).

In this case, the insulating stress transmission layer
2 is responsible for ensuring reliable and full
depletion of this stressed or stress-absorbing
semiconductor layer SA, with the result that in
addition to the improved charge carrier mobility all
the advantages of a fully depleted semiconductor
component are also obtained. Since the stress
transmission layer 2 also only includes a few atom
layers and, furthermore, in the case of CaF_2 and Si is
optimally matched in terms of its lattice constant, the
mechanical load or stress which is generated in the
stress generator layer SG is transmitted virtually
without losses to the stress-absorbing semiconductor
layer SA.

Then, in accordance with Figure 3A, a gate dielectric 3
and a control layer 4 are formed at the surface of the
stress-absorbing semiconductor layer SA. The gate
dielectric 3 may, for example, comprise conventional
gate dielectrics, such as for example silicon nitride,
silicon dioxide, ONO layer sequences or future new
high-k dielectrics, etc., whereas the control layer 4
may in the same way consist of conventional gate
materials, such as for example doped polysilicon or
metal.

However, it is preferable to use gate dielectrics with
a high dielectric constant or what are known as high-k
dielectrics as gate dielectric, in which case it is
preferable to deposit HfO_2, $HfSi_xO_y$, HfSiNO etc. once
again by means of an ALCVD or MOCVD process in a
thickness of typically 3 nanometers. On account of the
dramatic mismatch of the lattice constants of these

materials, i.e. of the gate dielectric, and on account of the low deposition temperatures for the stress-absorbing semiconductor layer SA, the deposition process takes place in amorphous form.

5

With regard to the gate material or control layer 4, what is known as a mid-gap material is deposited as gate material, in particular when full depletion of the active semiconductor body is desired. Materials of this
10   nature may favorably influence interactions with the high-k materials of the gate dielectric 3, in which case, in the case of the hafnium gate materials mentioned above, it is preferable to use a metal gate, such as for example TiN, as control layer 4.

15

Finally, in accordance with Figure 3B, both the control layer 4 and the gate dielectric 3 are patterned and source and drain regions S and D are in each case formed in the stress-absorbing semiconductor layer SA
20   in order to complete a field-effect transistor. The further steps involved in forming spacers, contact holes, connection regions, etc. correspond to the prior art, and consequently will not be described below.

25   In this way, it is possible to fabricate in particular semiconductor components with stressed or stress-absorbing semiconductor layers and/or semiconductor layers operating with full depletion in a simple and inexpensive way, with the result that in particular an
30   off-current is reduced and a charge carrier mobility and therefore clock rate of the semiconductor component are improved.

In the same way, it is possible, in particular when
35   using gate dielectrics with a high dielectric constant, to reduce the equivalent oxide thicknesses (EOT), with the result that the driving can be improved and in particular reduced voltages can be effected.

Furthermore, the insulating stress transmission layer reduces what are known as punch-through effects and in particular is able to reduce an off-state leakage
5   current considerably. In particular, however, a corresponding layer structure is now also available for sub-100 nanometer semiconductor components, allowing semiconductor components with only minor deviations in the electrical properties and with sufficient
10   reproducibility to be produced.

The invention has been described above on the basis of an nMOSFET. However, it is not restricted to this particular application and in the same way also
15   encompasses pMOSFETs or other semiconductor components with a stress-absorbing semiconductor layer. Furthermore, the invention has been described above on the basis of a stress-absorbing semiconductor layer consisting of silicon and a stress transmission layer
20   consisting of CaF_2. However, it is in the same way also possible to use alternative materials to produce these layers.